

**AMENDMENT UNDER 37 C.F.R. §1.312**

**Amendments to the Claims:**

- 6/2 to enter  
DB  
May 6/2001
1. (Currently amended) An emulsifiable polyolefin wax having sufficient functionality to be emulsifiable in an aqueous medium, a melt viscosity of less than 1,000 cps at 190°C, a Gardner color index of no greater than about 9, and an emulsion light transmittance of at least 20% at 525 nm with a 20 mm light [pathleng\*\*] pathlength in an emulsion comprising about 25 to about 35 wt % emulsifiable wax, about 60 to about 65 wt % water, a base sufficient to form an emulsion having a pH of between about 9 and about 10, and about 4 to about 10.5 wt % nonylphenol with 9 moles of [ethoxylatio,nsaid]ethoxylation, said emulsifiable polyolefin wax being prepared by reacting maleic anhydride with a starting material of either polypropylene or ethylene-propylene copolymer, wherein the amount of said maleic anhydride added to said starting material is about 0.1% to about 25 wt % of said starting material.
  2. (Previously presented) A composition comprising the emulsifiable polyolefin wax of claim 1.
  3. (Previously presented) The composition of claim 2, wherein said emulsion light transmittance is at least about 50%.
  4. (Canceled).
  5. (Previously presented) The composition of claim 2, wherein said emulsifiable polyolefin wax has a Mw of about 10,000 to about 20,000, and a melt viscosity of about 200 to about 800 cps.
  6. (Original) A floor polish comprising the composition of claim 1.
  7. (Original) A floor polish comprising the composition of claim 2.